

CONCRETE - SOLUTIONS

File No .:

9002

Final Report No.:

C-0323/US

Client:

US MIX Co.

112 South Santa Fe Drive

Denver, CO 80223 Attn: Andrew Beaty

Material:

AMX Mortar Type N

Subject:

Physical Properties Testing

Reference Specifications: ASTM C 1714: Standard Specification for Preblended Dry Mortar Mix for Unit Masonry

March 23, 2020

ASTM C 270: Standard Specification for Mortar for Unit Masonry

ASTM C 91: Standard Specification for Masonry Cement

Test Specifications:

ASTM C 109: Standard Test Method for Compressive Strength of Hydraulic Cement Mortars

(Using 2-in. or [50-mm] Cube Specimens)

ASTM C 185: Standard Test Method for Air Content of Hydraulic Cement Mortar

ASTM C 1437: Test Method for Flow of Hydraulic Cement Mortar

ASTM C 1506: Test Method for Water Retention of Hydraulic Cement-Based Mortars and

Plasters

Report of Test

Reported herein are test results made in C-Solutions Laboratory. All testing was performed in accordance with the specifications listed above and the procedures contained within those specifications requested by US MIX Co. Testing was performed in laboratory conditions of 73 \pm 3°F and a relative humidity of 50 \pm 4%.

Final Report No.: C-0323/US 2 of 2

Page:

Physical Properties - Table 1 AMX Mortar Type N

ASTM C 109	Test Result	Specification	<u>Status</u>
*Compressive Strength, PSI			
7 day 28 day *Average of three	1540 2050	NA 750 psi	NA Pass
ASTM C 185	Test Result		
Air Content, %	6	Max. 12%	Pass
ASTM C 1437	Test Result	Specification	Status
Flow, %	109	110 +/- 5%	Pass
ASTM C 1506	Test Result	Specification	Status
Water Retention, %	84.6	Min. 75%	Pass

Summary of test results:

This test report concludes AMX Mortar Type N comply with the requirements of ASTM C-270 Table 2 -Property Specification Requirements.

If you have any questions regarding this report or if we may be of further assistance, please do not hesitate to contact us directly.

Concrete Solutions, LLC

watto Vijeans Senior Chemist